## Vacuum Casting Polyurethane: 8263

## **Properties**

Ultimate tensile

68 N/mm<sup>2</sup>

strength

Heat deflection 80°C

Impact resistance

10 kJ/m<sup>2</sup>

Elongation at

15%

break

A rigid, superior strength white resin with excellent impact resistance. Can be coloured.

Certified fire retardant UL94V-0.

"Rigid. Industrial. Multi-purpose."

## **Example applications**



Housing



Air flow prototyping



Interior trim