Vacuum Casting Polyurethane: PT Flex 70 Liquid Rubber

Properties

Ultimate tensile

5 MPa

strength

Tear strength 22800 N/m

Shore Hardness 70A

Elongation at 175% break

A firm 70 Shore A fast-curing rubber. Excellent for casting decorative objects, production parts, tools, models, patterns, duplicate masters and more.

Can be pigmented or dyed.

"Fairly rigid, very strong."

Example applications



Oil seals



Rollers and casters



Stops and bungs