

# Digital Light Synthesis™ Resin: CE 221 - Cyanate Ester

## Properties

Ultimate tensile strength	92 ± 13 MPa
Elongation at break	3.3 ± 0.8%
Young's modulus	3870 ± 13 MPa
Heat deflection temperature	231°C


High performance material with excellent strength, stiffness and temperature resistance.

***"Perfect for applications that need long term thermal stability, like under-bonnet components"***

## Example applications



Cooling module



Fluid manifold



Drive gear



**PARAGON**  
Rapid Technologies

What do you want to  
make today?